



## OMG 35 - PRODUCT SPECIFICATION

Non-covered spheroid atomized aluminum powder used in aluminothermia, epoxy resins, exothermal products, siderurgy, metallurgy and alike.

Chemical Composition	Unit	Essay	Average	
			Minimum	Maximum
ALUMINUM(Al)	%	ASTM E 1024-84	98,50	
IRON(Fe)	%	ASTM E 1024-84		1,00
SILICIUM(Si)	%	ASTM E 34-88		0,50
COPPER(Cu)	%	ASTM E 1024-84		0,25
ZINC(Zn)	%	ASTM E 1024-84		0,20
MAGNESIUM(Mg)	%	ASTM E 1024-84		0,60
MANGANESE(Mn)	%	ASTM E 1024-84		0,60
NICKEL(Ni)	%	ASTM E 1024-84		0,10
LEAD(Pb)	%	ASTM E 1024-84		0,05

GRANULOMETRY (STANDARD)		Unit	Essay	Minimum	Maximum
Mesh	100% 16-Mesh Strainer	%	ASTM B 214-92		
Mesh	0-10% 325-Mesh Strainer	%	ASTM B 214-92		
Mesh		%	ASTM B 214-92		
Mesh		%	ASTM B 214-92		
Mesh		%	ASTM B 214-92		

### APPARENT DENSITY

Unit	Essay	Minimum	Maximum
(g/cm <sup>3</sup> )	ASTM B 329-90	0,8	1,2

### STANDARD PACKAGING

<b>EOM 25:</b> 25 kg bags.
<b>EOM 1000:</b> Big Bag from 1,000 kg to 1,200 kg.